

Automotive ventilation pipes, dust caps

| Product | Appearance | Density (g/cm ³) | Tensile strength (MPa) | Elong. at break (%) | Shore hardn. 10s,23°C | Tear str. (kN/m) | Comp. set 22h@70°C (%) |
|-------------------------|----------------|---------------------------------|------------------------------|------------------------|--------------------------|---------------------|------------------------------|
| TPV H721-70A | Black granules | 0.93 | 6.3 | 600 | 54 (A) | 29 | 29 |
| TPV 12-80A | Black granules | 0.95 | 13.7 | 622 | 90 (A) | 93 | 46 |
| TPV 721-93A | Black granules | 0.95 | 22.3 | 830 | 48 (D) | 138 | 60 |
| | | ASTM D-792 | ASTM D-412 | ASTM D-412 | ASTM D-2240 | ASTM D-624 | ASTM D-395 |