

Sealing and profile grades

Product	Appearance	Density (g/cm ³)	Tensile strength (MPa)	Elong. at break (%)	Shore hardn. 10s,23°C	Tear str. (kN/m)	Comp. set 22h@70°C (%)
TPV 14-50A	Black granules	0.93	4.5	600	55 (A)	25	25
TPV 10-60A	Black granules	0.97	5.3	400	63 (A)	27	28
TPV T18-75A	Black granules	0.90	8.1	600	75 (A)	46	45
		ASTM D-792	ASTM D-412	ASTM D-412	ASTM D-2240	ASTM D-624	ASTM D-395