

UPM BioMotion™	X10	X20	X40
STSA Oberfläche [m²/g]	11	23	40
pH	6 - 10	6 - 10	6 - 10
Schwefelgehalt [%]	< 0.2	< 0.2	< 0.2
Benzo[a]pyren [ppm]	< 0.1	< 0.1	< 0.1
Jede der 22 FDA-PAKs [ppm]	< 1	< 1	< 1
Trocknungsverlust [%]	< 3	< 3	< 3