

LUVOMAXX® -BC-Carcassruße

Produkt	ASTM	N-539	N-550	N-650	N-660	N-772
Öl Adsorption (ml/100g)	D 2414	111	121	122	90	65
Iodzahl (mg/g)	D 1510	43	43	36	36	30
Asche (% max.)	D 1506	0,5	0,5	0,5	0,5	0,5
Siebrückstand 325 mesh (ppm max.)	D 1514	100	200	250	250	500
Stickstoffoberfläche (m²/g)	D 6556	38	40	36	35	32
Lieferform	-	Perlen	Perlen	Perlen	Perlen	Perlen