

## LUVOMAXX® -BC-Treadruße

Produkt	ASTM	N-326	N-330	N-339	N-347	N-375
<b>Öl Adsorption (ml/100g)</b>	D 2414	72	102	120	124	114
<b>Iodzahl (mg/g)</b>	D 1510	82	82	90	90	90
<b>Asche (% max.)</b>	D 1506	0,5	0,5	0,5	0,5	0,5
<b>Siebrückstand 325 mesh (ppm max.)</b>	D 1514	350	200	500	200	250
<b>Stickstoffoberfläche (m<sup>2</sup>/g)</b>	D 6556	78	82	90	85	93
<b>Lieferform</b>	-	Perlen	Perlen	Perlen	Perlen	Perlen