

LUVOMAXX® -BC-Treadruße

Produkt	ASTM	N-115	N-121	N-134	N-220	N-234
Öl Adsorption (ml/100g)	D 2414	113	131	127	114	125
Iodzahl (mg/g)	D 1510	160	121	142	121	120
Asche (% max.)	D 1506	0,5	0,5	0,5	0,5	0,5
Siebrückstand 325 mesh (ppm max.)	D 1514	500	250	250	250	200
Stickstoffoberfläche (m ² /g)	D 6556	137	122	143	119	119
Lieferform	-	Perlen	Perlen	Perlen	Perlen	Perlen