

## LUVOMAXX® Flammruße

	ASTM	LB/P	LB/S
<b>Öl Adsorption (ml/100g)</b>	D 2414	100	95
<b>Iodzahl (mg/g)</b>	D 1510	14	30
<b>pH-Wert</b>	D 1512	0,5	0,5
<b>Asche (% max.)</b>	D 1506	0,1	0,1
<b>Siebrückstand @ 325 mesh (ppm)</b>	D 1514	7	6 - 11
<b>Schüttdichte (kg/m<sup>3</sup>)</b>	D 1513	400	200
<b>Lieferform</b>	-	Perlen	Pulver