

## LUVOMAXX® Thermalruße

	<b>ASTM Methode</b>	<b>MT N-990</b>	<b>MT N-991</b>
<b>Öl Adsorption (ml/100g)</b>	D 2414	40	40
<b>Iodzahl (mg/g)</b>	D 1510	8	8
<b>pH-Wert</b>	D 1512	9	9
<b>Asche (% max.)</b>	D 1506	0,1	0,1
<b>Siebrückstand @ 325 mesh (ppm)</b>	D 1514	27	34
<b>Schüttdichte (kg/m<sup>3</sup>)</b>	D 1513	500	360
<b>Lieferform</b>	-	Perlen	Pulver