

<b>Copolymer</b>	<b>Gehalt Propylen (Gew-%)</b>	<b>Mooney-Viskosität ML (1+4) @125°C</b>	<b>Ölgehalt (Gew-%)</b>
DUTRAL® CO 034	28	44	-
DUTRAL® CO 038	28	60	-
DUTRAL® CO 043	45	33	-
DUTRAL® CO 054	41	44	-
DUTRAL® CO 058	48	80	-
DUTRAL® CO 059	41	79	-