

Dichtungen und Profile

Produkt	Lieferform	Dichte (g/cm ³)	Zug- festigkeit (MPa)	Bruch- dehnung (%)	Shore Härte 10s,23°C	WRW (kN/m)	DVR 22h@70°C (%)
TPV 14-50A	Schwarzes Granulat	0,93	4,5	600	55 (A)	25	25
TPV 10-60A	Schwarzes Granulat	0,97	5,3	400	63 (A)	27	28
TPV T18-75A	Schwarzes Granulat	0,90	8,1	600	75 (A)	46	45
		ASTM D-792	ASTM D-412	ASTM D-412	ASTM D-2240	ASTM D-624	ASTM D-395