

Flexible Verbindungen, Distanzleisten, Distanzstücke

Produkt	Lieferform	Dichte (g/cm ³)	Zug- festigkeit (MPa)	Bruch- dehnung (%)	Shore Härte 10s,23°C	WRW (kN/m)	DVR 22h@70°C (%)
TPV 11-64A	Schwarzes Granulat	0,97	6,6	554	64 (A)	22	21
TPV 810-80A	Schwarzes Granulat	0,97	10,2	578	83 (A)	53	38
TPV 814-40D	Schwarzes Granulat	0,97	13,5	684	41 (D)	109	30
		ASTM D-792	ASTM D-412	ASTM D-412	ASTM D-2240	ASTM D-624	ASTM D-395