

Spritzguss-Anwendungen

Produkt	Lieferform	Dichte (g/cm ³)	Zug- festigkeit (MPa)	Bruch- dehnung (%)	Shore Härte 10s,23°C	WRW (kN/m)	DVR 22h@70°C (%)
TPV 10-45A	Schwarzes Granulat	0,95	4,2	450	45 (A)	20	38
TPV 10-80A	Schwarzes Granulat	0,94	7,5	450	83 (A)	42	40
TPV 11-73A	Schwarzes Granulat	0,96	7,5	400	74 (A)	36	35
TPV 11-80A	Schwarzes Granulat	0,96	11,1	550	82 (A)	40	33
TPV 11-50D	Schwarzes Granulat	0,93	24	700	50 (D)	113	n.a.
		ASTM D-792	ASTM D-412	ASTM D-412	ASTM D-2240	ASTM D-624	ASTM D-395