

Kabel und Drähte

Produkt	Lieferform	Dichte (g/cm ³)	Zug- festigkeit (MPa)	Bruch- dehnung (%)	Shore Härte 10s,23°C	WRW (kN/m)	DVR 22h@70°C (%)
TPV H721-70A	Schwarzes Granulat	0,97	7,5	550	70 (A)	40	30
TPV 12-80A	Schwarzes Granulat	1,21	7,3	450	83 (A)	42	45
TPV 721-93A	Schwarzes Granulat	0,96	13	600	93 (A)	65	50
		ASTM D-792	ASTM D-412	ASTM D-412	ASTM D-2240	ASTM D-624	ASTM D-395