

Lösungs-Styrol-Butadien Kautschuk (SSBR)

Lösungs-Styrol-Butadien-Kautschuk (SSBR)	Type	Styrolgehalt (%)	Vinylgehalt (%)	Mooney-Viskosität ML(1+4) @100°C	Ölgehalt phr
Europrene®	SOL B 1205	26		50	-
Europrene®	SOL R 72614	25	64	55	37.5 TDAE
Europrene®	SOL R C2525	26	24	54	-