

## Pure substances

Product	Appearance	Active ingredient	Melting point (onset)
<b>LUVOMAXX® 6PPD</b>	Dark brown granules	N-(1,3-dimethylbutyl)-N'-phenyl-p-phenylenediamine	50 °C
<b>LUVOMAXX® BHT</b>	White powder	2,6-di-tert-butyl-4-methylphenol	68 °C
<b>LUVOMAXX® BHP</b>	Light yellow powder	2,2-Methylene-bis-(4-methyl-6-tert-butyl phenol)	124 °C
<b>LUVOMAXX® CDPA</b>	White powder	4,4'-bis-(1,1-dimethylbenzyl)- diphenylamine	99 °C
<b>LUVOMAXX® DTPD</b>	Brownish flakes	N,N'-ditolyl-p-phenylenediamine	93 °C
<b>LUVOMAXX® IPPD</b>	Dark brown granules	N-isopropyl-N'-phenyl -p-phenylenediamine	75 °C
<b>LUVOMAXX® MBI/OC</b>	Oil-coated powder	2-Mercaptobenzimidazole	295 °C
<b>LUVOMAXX® MMBI/OC</b>	Oil-coated powder	4- /5-methyl mercaptobenzimidazole	270 °C
<b>LUVOMAXX® ODPA</b>	Brownish powder	4,4'-dioctyl diphenylamine	85 °C
<b>LUVOMAXX® SDPA</b>	Highly viscous amber liquid	Styrenated diphenylamine	- 5 °C
<b>LUVOMAXX® TMQ</b>	Amber granules	Polymeric 2,2,4-trimethyl-1,2-dihydro-quinoline	80 °C