

## Deformation joints, shims, spacers

Product	Appearance	Density (g/cm <sup>3</sup> )	Tensile strength (MPa)	Elong. at break (%)	Shore hardn. 10s,23°C	Tear str. (kN/m)	Comp. set 22h@70°C (%)
<b>TPV 11-64A</b>	Black granules	0.97	6.6	554	64 (A)	22	21
<b>TPV 810-80A</b>	Black granules	0.97	10.2	578	83 (A)	53	38
<b>TPV 814-40D</b>	Black granules	0.97	13.5	684	41 (D)	109	30
		ASTM D-792	ASTM D-412	ASTM D-412	ASTM D-2240	ASTM D-624	ASTM D-395