

Wire and cable grades

Product	Appearance	Density (g/cm ³)	Tensile Strength (MPa)	Elong. at Break (%)	Shore hardn. 10s,23°C	Tear str. (kN/m)	Comp. set 22h@70°C (%)
TPV H721-70A	Black granules	0.97	7.5	550	70 (A)	40	30
TPV 12-80A	Black granules	1.21	7.3	450	83 (A)	42	45
TPV 721-93A	Black granules	0.96	13	600	93 (A)	65	50
		ASTM D-792	ASTM D-412	ASTM D-412	ASTM D-2240	ASTM D-624	ASTM D-395