

| <b>Product</b>                 | <b>Appearance</b> | <b>Specific surface area<br/>BET<br/>[m<sup>2</sup>/g]</b> | <b>Sieve residue<br/>&gt; 45µm<br/>[%]</b> | <b>pH value</b> |
|--------------------------------|-------------------|--|--|-----------------|
| <b>LUVOMAXX® Silica HM 200</b> | White powder      | 170 - 230  | ≤ 0.05                                     | 3.6 - 4.5       |
| <b>LUVOMAXX® Silica HM 300</b> | White powder      | 270 - 330  | ≤ 0.05                                     | 3.6 - 4.5       |
| <b>LUVOMAXX® Silica HM 380</b> | White powder      | 350 - 410  | ≤ 0.05                                     | 3.6 - 4.5       |