

Polymer-bound preparations

Product	Appearance	Active ingredient	Gas yield (ml/g)	Decomp. temperature (°C)	Carrier
LUVOMAXX® AZ GR	Yellow granules	Azodicarbonamide (75%)	220	200	EPM
LUVOMAXX® OB GR	White granules	4,4'-Oxybis (benzene sulfonylhydrazide) (75%)	100	160	EPM