

Product	Appearance	Properties and applications	Volatile matter (%)	TG	Mooney ML (1+4) @ 100°C
<b>LUVOMAXX 3,4 Polyisoprene</b>	Bales	<ul style="list-style-type: none"><li>• Very good mechanical damping/ sound damping properties</li><li>• Improved grip and wet grip</li><li>• Straightforward co-vulcanization in blends with NR and SBR.</li></ul> Car and truck tyres, soles for climbing, walking and safety boots, sailing shoes, golfing items, car sports seats, insulation materials for cars, machinery as well as household and office appliances	< 0.5	- 10 °C	65 - 75