

Wire and cable grades

| Product | Appearance | Density (g/cm ³) | Tensile Strength (MPa) | Elong. at Break (%) | Shore hardn. 10s,23°C | Tear str. (kN/m) | Comp. set 22h@70°C (%) |
|-------------------------|----------------|---------------------------------|------------------------------|------------------------|--------------------------|---------------------|------------------------------|
| TPV H721-70A | Black granules | 0.97 | 7.5 | 550 | 70 (A) | 40 | 30 |
| TPV 12-80A | Black granules | 1.21 | 7.3 | 450 | 83 (A) | 42 | 45 |
| TPV 721-93A | Black granules | 0.96 | 13 | 600 | 93 (A) | 65 | 50 |
| | | ASTM D-792 | ASTM D-412 | ASTM D-412 | ASTM D-2240 | ASTM D-624 | ASTM D-395 |