

## LUVOMAXX® BC Tread Grades

	<b>ASTM</b>	<b>N-115</b>	<b>N-121</b>	<b>N-134</b>	<b>N-220</b>	<b>N-234</b>
<b>Oil adsorption (ml/100g)</b>	D 2414	113	131	127	114	125
<b>Iodine no. (mg/g)</b>	D 1510	160	121	142	121	120
<b>Ash content (% max.)</b>	D 1506	0,5	0,5	0,5	0,5	0,5
<b>Sieve residue 325 mesh (ppm max.)</b>	D 1514	500	250	250	250	200
<b>Nitrogen surface area (m<sup>2</sup>/g)</b>	D 6556	137	122	143	119	119
<b>Appearance</b>	-	black pellets	black pellets	black pellets	black pellets	black pellets