

<b>Copolymer</b>	<b>Propylene Content (% wt)</b>	<b>Viscosity Mooney ML (1+4) 125°C</b>	<b>Oil Content (% wt)</b>
DUTRAL® CO 034	28	44	-
DUTRAL® CO 038	28	60	-
DUTRAL® CO 043	45	33	-
DUTRAL® CO 054	41	44	-
DUTRAL® CO 058	48	80	-
DUTRAL® CO 059	41	79	-