

LUVOMAXX® Conductive blacks

Product	Iodine Absorption Number [mg/g] acc. to ASTM D 1510	Oil Adsorption Number [ml/100g] acc. to ASTM D 2414	Tint strength acc. to ASTM D 3265
LUVOMAXX® M 450*	125 ± 8	111 ± 8	115 ± 8
LUVOMAXX® M 451*	125 ± 8	92 ± 8	120 ± 8
LUVOMAXX® M 360	70 ± 8	123 ± 8	85 ± 8
LUVOMAXX® M 361	45 ± 8	117 ± 8	60 ± 8
LUVOMAXX® M 3810	51 ± 8	122 ± 8	55 ± 8
LUVOMAXX® M 3710	68 ± 8	126 ± 8	60 ± 8

* grades with sieve residue (@325 mesh) of max. 10 ppm, all other grades show typical sieve residue of max 20 ppm