

## Automotive parts, moulded goods

Product	Appearance	Density (g/cm <sup>3</sup> )	Tensile strength (MPa)	Elong. at break (%)	Shore hardn. 10s,23°C	Tear str. (kN/m)	Applications
<b>TPV 830-62A</b>	Black granules	0.93	5.5	450	58 (A)	25	Covers
<b>TPV 10-35D</b>	Black granules	0.95	15.1	634	36 (D)	91	Side airbags
<b>TPV 14-40D</b>	Black granules	0.94	15	580	42 (D)	96	Hub caps
		ASTM D-792	ASTM D-412	ASTM D-412	ASTM D-2240	ASTM D-624	-