

<b>Product</b>	<b>Appearance</b>	<b>Specific surface area BET [m<sup>2</sup>/g]</b>	<b>Sieve residue &gt; 45µm [%]</b>	<b>pH value</b>
<b>LUVOMAXX® Silica HM 200</b>	White powder	170 - 230	≤ 0.05	3.6 - 4.5
<b>LUVOMAXX® Silica HM 300</b>	White powder	270 - 330	≤ 0.05	3.6 - 4.5
<b>LUVOMAXX® Silica HM 380</b>	White powder	350 - 410	≤ 0.05	3.6 - 4.5