

Pure substances

Product	Appearance	Active ingredient	Melting point (onset)
LUVOMAXX® 6PPD	Dark brown granules	N-(1,3-dimethylbutyl)-N'-phenyl-p-phenylenediamine	50 °C
LUVOMAXX® BHT	White powder	2,6-di-tert-butyl-4-methylphenol	68 °C
LUVOMAXX® BHP	Light yellow powder	2,2-Methylene-bis-(4-methyl-6-tert-butyl phenol)	124 °C
LUVOMAXX® CDPA	White powder	4,4'-bis-(1,1-dimethylbenzyl)- diphenylamine	99 °C
LUVOMAXX® DTPD	Brownish flakes	N,N'-ditolyl-p-phenylenediamine	93 °C
LUVOMAXX® IPPD	Dark brown granules	N-isopropyl-N'-phenyl -p-phenylenediamine	75 °C
LUVOMAXX® MBI/OC	Oil-coated powder	2-Mercaptobenzimidazole	295 °C
LUVOMAXX® MMBI/OC	Oil-coated powder	4- /5-methyl mercaptobenzimidazole	270 °C
LUVOMAXX® ODPA	Brownish powder	4,4'-dioctyl diphenylamine	85 °C
LUVOMAXX® SDPA	Highly viscous amber liquid	Styrenated diphenylamine	- 5 °C
LUVOMAXX® TMQ	Amber granules	Polymeric 2,2,4-trimethyl-1,2-dihydro-quinoline	80 °C